


Technical Data



| | Standard | Result |
|-----------------------------------|--|---|
| Thickness | | 2mm |
| Wear layer | | 0.3mm |
| Guarantee | Commercial Domestic | 10 Years* 12 Years* |
| Bevelled edge | | No |
| Standards | EN 649 ASTM F1700 | |
| Classification | EN 685 EN 685 ASTM F1700 | 31: Commercial moderate 23: Domestic heavy Class III Type B |
| Reaction to fire | EN 13501-1 EN ISO 9239-1 EN ISO 11925-2 ASTM E648-06 | B _{fl} -s1 Pass Pass Class 1 |
| Slip resistance | EN 13893 BS 7976 DIN 51130 ASTM C1028 | DS |
| Staining resistance | EN 423 ASTM F925 | Class 0 Pass |
| Light fastness | EN ISO 105-B02 ASTM F1515 | ≥ 6 < 8 |
| Abrasion resistance | EN 660-2 ASTM D3884 | Group T Pass |
| Dimensional stability | EN 434 ASTM F2199 | ≤ 0.25% Pass |
| Acoustic impact noise reduction | EN ISO 717-2 EN ISO 140-8 | ΔL _w = 1 dB |
| Electrical behaviour body voltage | EN 1815 | Pass |
| Indentation – residual | EN 433 | ≤ 0.1mm |
| Castor chair continuous use | EN 425 | Pass |
| Thermal conductivity | ISO 8302 | 0.0100m ² K/W Suitable for underfloor heating. Max 27°C |
| Light reflectance value | BS 8493:2008+AI:2010 | See website for LRV results |
| Adhesive | Karndean Universal Acrylic Epoxy High Temperature Pressure Sensitive | Yes Yes Yes Yes Yes |
| Recycling | | Suitable |

| Product Code | Size (mm) | Slip Resistance | | |
|--|-----------|-----------------|--------------|-----------|
| | | BS7976 (dry) | BS7976 (wet) | DIN 51130 |
| ST5, ST8, ST9, ST10, T98, T99, T100, T101, T102 | 305 x 305 | 65 | 40 | R10 |
| T88, T89 | | 64 | 34 | |
| KP45 | 915 x 102 | 64 | 40 | |
| KP94, KP96, KP97, KP98, KP99, KP102, KP103, KP105 | 915 x 152 | 63 | 38 | R9 |
| T74, T90 | 305 x 305 | 66 | 27 | |
| ST11, ST12, ST13, ST14 | 305 x 457 | | | |
| KP32, KP38 KP39, KP40, KP51, KP52, KP55, KP67, KP68, KP70, KP91, KP92, KP93, KP107 | 915 x 102 | 65 | 36 | |

*Subject to terms



For more information:

Call: 01386 820104

Email: commercial@karndean.co.uk

Visit: www.karndean.co.uk

