























# Technical Data

	Standard	Result
	Thickness	4.5mm
	Wear layer	0.55mm
	Guarantee	Light Industrial Commercial Domestic
		10 Years* 12 Years* 15 Years*
	Bevelled edge	No
	Standards	EN 649 ASTM F1700
	Classification	EN 685
		EN 685
		EN 685
		ASTM F1700
		42: Light industrial general 33: Commercial heavy 23: Domestic heavy Class III Type B
	Reaction to fire	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2 ASTM E648-06
		B <sub>fl</sub> -s1 Pass Pass Class 1
	Slip resistance	EN 13893 BS 7976 DIN 51130 ASTM C1028
		DS
	Staining resistance	EN 423 ASTM F925
		Class 0 Pass
	Light fastness	EN ISO 105-B02 ASTM F1515
		≥ 7 < 8
	Abrasion resistance	EN 660-2 ASTM D3884
		Group T Pass
	Dimensional stability	EN 434 ASTM F2199
		≤ 0.25% Pass
	Acoustic impact noise reduction	EN ISO 717-2 EN ISO 140-8
		ΔL <sub>w</sub> = 13 dB
	Electrical behaviour body voltage	EN 1815
		Pass
	Indentation – residual	EN 433
		≤ 0.1mm
	Castor chair continuous use	EN 425
		Pass
	Thermal conductivity	ISO 8302
		0.0245m <sup>2</sup> K/W Suitable for underfloor heating. Max 27°C
	Light reflectance value	BS 8493:2008+A1:2010
		See website for LRV results
	Adhesive	
		Most applications will not require the use of adhesives. Under extreme conditions please refer to our installation instructions.
	Recycling	Suitable

Product Code	Size (mm)	Slip Resistance		
		BS7976 (dry)	BS7976 (wet)	DIN 51130
LLT200, LLT201, LLT202, LLT203	500 x 610	66	29	R9
LLP92, LLP101, LLP102, LLP103, LLP104, LLP105, LLP106	1050 x 250	61	33	



[\\*Subject to terms](#)

For more information:

**Call:** 01386 820104

**Email:** commercial@karndean.co.uk

**Visit:** www.karndean.co.uk



Karndean  
LooseLay