

Technical Data



	Standard	Result
Thickness	3/32" (2.5mm)	
Wear layer	20 mil (0.5mm)	
Guarantee	Commercial 6 Years* Domestic 12 Years*	
Bevelled edge	No	
Standards	EN 649 ASTM F-1700	
Classification	EN 685:41 Light industrial moderate EN 685:32 Commercial general EN 685.23 Domestic heavy ASTM F1700 Class 3 Type B	
Reaction to fire	EN 13501-1 ISO 9239-1 ISO 11925-2 ASTM E-648-06	Bfl-S1 Pass Pass Class 1
Slip resistance	EN 13893 DIN 51130 BS 7976 AS/NZS 4586 ASTM C-1028	DS
Staining resistance	EN 423 ASTM F-925	Class 0 Pass
Light fastness	ISO 105-B02 ASTM F-1515	≥ 7 < 8
Abrasion resistance	EN 660-2 ASTM 3884	Group T Pass
Dimensional stability	EN 434 ASTM F-2199	≤ 0.25% Pass
Acoustic impact noise reduction	EN ISO 717-2 EN ISO 140-8	ΔLw= 1 db
Electrical behaviour body voltage	EN 1815 AATCC 134-1996	Pass Pass
Indentation – residual	EN 433 ASTM F-1914	≤ 0.1mm < 8%
Castor chair continuous use	EN 425 ASTM D-3884	Pass Pass
Thermal conductivity	ISO 8302 Suitable for underfloor heating	0.0120m²K/W
Adhesive	Acrylic Epoxy HT [High Temperature] PS [Pressure Sensitive]	Yes Yes Yes Yes
Recycling		Suitable

Product Code	Size (mm)	Slip Resistance	
		BS7976 (dry)	BS7976 (wet)
MLC01	16" x 16" (406mm x 406mm)	62	20
MLC07, MLC08		50	26
MX92, MX93, MX95, MX97, MX98	12" x 12" (305mm x 305mm)	69	23
MS1, MS2		59	25
MP2, MP3, MP4	36" x 6" (915mm x 152mm)	61	31



*Subject to terms

For more information:

Call: 888-266-4343

Email: info@karndean.com

Visit: www.karndean.com



Your space. Your needs. Your style.