



# Technical Data



	Standard	Result
Thickness		3.0 mm (1/8")
Wear layer		0.7 mm (30 mil)
Warranty	Commercial	15 years*
	Residential	20 years*
Beveled edge		Yes
Standards	ASTM F1700	
Classification	ASTM F1700	Class III Type B
Reaction to fire	ASTM E648-06	Class 1
Flammability test	FF 1-70; Federal Approval	Pass
Slip resistance	ASTM C1028	ADA compliant Dry 0.68 Wet 0.66
Staining resistance	ASTM F925	Pass
Light fastness	ASTM F1515	Pass $\Delta E = 3.3$
Abrasion resistance	ASTM D3884	115,000 cycles
Dimensional stability	ASTM F2199	Pass -0.002"/lin.ft
Static load	ASTM F970	1,000 psi
Flexibility	ASTM F137	Pass
Adhesive		K-91A K-87WS K-91P (HMT) Karndean Epoxy
Recycling		Suitable

\*Subject to terms

For more information:  
**Call:** 888-266-4343  
**Email:** info@karndean.com  
**Visit:** www.karndean.com

Manufactured to:

