

## **Technical Data**



	Standard	Result
Thickness		3.0 mm (1/8")
Wear layer		0.5 mm (20 mil)
Warranty	Commercial	10 years*
	Residential	15 years*
Beveled edge		No
Standards	ASTM F1700	
Classification	ASTM F1700	Class III Type B
Reaction to fire	ASTM E648-06	Class 1
Flammability test	FF 1-70; Federal Approval	Pass
Slip resistance	ASTM C1028	ADA compliant
		Dry 0.68
		Wet 0.66
Staining resistance	ASTM F925	Pass
Light fastness	ASTM F1515	Pass
		ΔE = 3.3
Abrasion resistance	ASTM D3884	115,000 cycles
Dimensional stability	ASTM F2199	Pass
		-0.002"/lin.ft
Static load	ASTM F970	1,000 psi
Flexibility	ASTM F137	Pass
Adhesive		K-91A
		K-87WS
		K-91P (HMT)
		Karndean Epoxy
Recycling		Suitable

<sup>\*</sup>Subject to terms

For more information: Call: 888-266-4343

Email: info@karndean.com Visit: www.karndean.com



## Manufactured to:





