


# Technical Data



	Standard	Result	Product	Size (mm)	Slip Resistance Oil-Wet Ramp
<b>Size</b>	ISO 24342	See separate table	CER11	457 X 305	R10
<b>Thickness</b>	ISO 24346	3.0 mm	CER12	457 X 305	R10
<b>Wear Layer</b>		0.7 mm	CER13	457 X 305	R10
<b>Surface treatment</b>		K-Guard+ PU coating	CER14	457 X 305	R10
<b>Warranty</b>	Commercial	20 years wear*	CER15	457 X 305	R10
	Domestic	Lifetime wear*	CER16	457 X 305	R10
<b>Bevelled Edge</b>		Yes	CER17	457 X 305	R10
<b>Standards</b>	EN 649/EN ISO 10582	Pass	CER18	457 X 305	R10
	ASTM F1700	Pass	CER19	457 X 305	R10
<b>Classification</b>		Commercial Very Heavy Duty use	CER20	457 X 305	R10
		Domestic Extra Heavy Duty use	CER21	457 X 305	R10
<b>Staining Resistance</b>	EN 423	Class 0	M45	457 X 305	R9
	ASTM F925	Pass	RP73	915 X 76	R9
<b>Colour Fastness to Light</b>	ISO 105-B02	≥6	RP91	915 X 76	R9
	ASTM F1515	<8	RP94	915 X 76	R9
<b>Abrasion Resistance</b>	EN 660-2	Group T	RP95	915 X 76	R9
	ISO 10582	Type 1	RP96	915 X 76	R9
	ASTM D3884	Pass	RP97	915 X 76	R9
<b>Flexibility</b>	ISO 24344	Pass	RP98	915 X 76	R9
<b>Dimensional stability</b>	EN 434/ ISO 23999	≤ 0.25%	RP99	915 X 76	R9
	ASTM F2199	Pass	RP100	915 X 76	R9
<b>Acoustic Impact noise reduction</b>	EN ISO 717-2 / EN ISO 140-8	ΔL <sub>w</sub> = 2 dB**	RP101	915 X 76	R9
<b>Electrical behaviour body voltage</b>	EN 1815	Pass	RP102	915 X 76	R9
<b>Indentation - residual</b>	EN 433/ EN ISO 24343-1	≤ 0.1mm	RP103	915 X 76	R9
	ASTM F1914	<8%	RP104	915 X 76	R9
<b>Castor chair continuous use</b>	EN 425/ ISO 4918	Pass	RP105	915 X 76	R9
<b>Thermal resistance</b>	ISO 8302	0.0147 m <sup>2</sup> K/W Suitable for underfloor heating			
<b>Reaction to Fire</b>	AS/NZS 9239.1:2003	CRF: 9.1 kW/m <sup>2</sup> Smoke value: 105 % min.			
<b>***Slip resistance</b>	AS/NZS 4586:2013	See separate table			
<b>Adhesive</b>	General use:	Karndean Mega-Bond			
	High temperature:	Karndean 8000 2-part Polyurethane			
<b>Recycling</b>		Suitable			
<b>Environmental</b>	GBCA/NZGBC GreenStar Rating System	GreenTag Level 'A'; LCA Silver Plus; Best Practice PVC			
<b>Phthalate free</b>		Yes			

\*Subject to terms

\*\*Result is Ln,w = 58 dB when installed on Regupol 4515 acoustic underlay

\*\*Slip resistance is measured on ex-factory product. Slip resistance in use will be affected by surface contamination and by how the product is maintained

### For more information:

#### Australia

Call: 1800 33 11 70

Email: customerservice@karndean.com.au

Visit: www.karndean.com

#### New Zealand

Call: 0800 44 21 01

Email: customerservice@karndean.co.nz

Visit: www.karndean.com

Manufactured to ISO9001



green building council australia  
MEMBER 2013-2014

