



# Technical Data



	Standard	Result
Thickness		6.5 mm
Size		48.03" x 7.05"
Locking system*		2G™ angling installation
Wear layer		20 mil (0.50 mm)
Surface treatment		K-Guard+ PU coating
Warranty**	Commercial Residential	15 years Lifetime
Bevelled edge		Micro
Standards	ASTM F3261	Pass:-Resilient flooring with Rigid Polymeric Core
Reaction to fire	ASTM E648-06	Class 1
Flammability	FF 1-70; Federal Approval	Pass
Slip resistance***	ASTM D2047	Pass (Dry >0.8)
Staining resistance	ASTM F925	Pass (No change)
Light fastness	ASTM F1515	Pass
Electrostatic propensity	AATCC 134	-1.4 kV
Abrasion resistance	ASTM D4060	Pass 20 000 cycles
Dimensional stability	ASTM F2199	Pass (width -0.003"/lin.ft) Pass (length -0.003"/lin.ft)
Static Load	ASTM F970	Pass 650 psi at 0.005"
Small ball impact	NALFA 3.6	Pass class 4
Large ball impact	NALFA 3.5	Pass class 4
Acoustic impact noise reduction	ASTM E2179-09 ASTM E492-09	ΔIIC = 21 dB IIC = 69 dB (6" Concrete Slab w/Drop Ceiling) IIC = 71 dB (6" Slab w/Drop Ceiling + QuietChoice)
Indentation-residual	ASTM F 1914	Pass
Thickness swell	NALFA 3.2	Pass class 4
Chair resistance	NALFA 3.9	Pass class 4
Surface bond	NALFA 3.10	Pass class 4
Thermal resistance	ISO8302	0.052 m <sup>2</sup> K/W suitable for underfloor heating max 81 °F
Adhesive		None required; please install according to our installation instructions.
Environmental	Floorscore SCS-EC10.3-2014 v4.0 NSF/ANSI 332 Assure certified ISO 14001 / ISO 9001	Indoor air quality certified; Compliant low emitting VOC emissions. Sustainability Assessment for Resilient Floor Coverings; Silver certified product Conformance with Rigid Core Flooring Standard SCS-0011 V1-0 Manufactured to quality and environment management systems standards
Recycling		Suitable
Phthalate free		Yes

\*2G™ is a patented technology invented by Välinge Innovation AB. The 2G™ word mark and logo are registered trademarks owned by Välinge Innovation AB and any use of such marks is under license.

\*\*Subject to terms.

\*\*\*Slip resistance is measured on freestanding ex-factory product. Slip resistance can be affected by many factors including but not limited to: product installation and underlayment, surface contamination, use, wear and how the product is maintained. Textural variation along the surface of the product can affect nominal values.

For more information:

Call: 888-266-4343

Email: [info@karndean.com](mailto:info@karndean.com)

Visit: [www.karndean.com](http://www.karndean.com)

Size	Box quantity
48.03" x 7.05"	10 planks / 23.51 sq.ft

Jul-20

