

	Standard	Result	
		3mm	2.5mm
Size	EN ISO 24342	Various	Various
Thickness	EN ISO 24346	3.0 mm	2.5 mm
Wear layer	EN ISO 24340	0.7 mm	0.55 mm
Surface treatment		K-Guard+ PU coating	K-Guard+ PU coating
Guarantee <sup>1</sup>	Light industrial	20 years	15 years
	Commercial	20 years	15 years
	Residential	Lifetime guarantee	Lifetime guarantee
Mass per unit area	EN ISO 23997	5220 g/m <sup>2</sup>	4335 g/m <sup>2</sup>
Standards	EN 649/EN ISO 10582	Pass	Pass
Classification	EN 685/EN ISO 10874 - Light industrial	43: Light industrial heavy	41: Light industrial general
	EN 685/EN ISO 10874 - Commercial	34: Commercial very heavy	32: Commercial moderate
	EN 685/EN ISO 10874 - Domestic	23: Domestic heavy	23: Domestic heavy
Reaction to fire	EN 13501-1	B <sub>fl</sub> -s1	B <sub>fl</sub> -s1
Staining resistance	EN ISO 26987/EN 423	Excellent	Excellent
Light fastness	EN ISO 105-B02	Pass (≥ 6)	Pass (≥ 6)
Abrasion resistance	EN 660-2	Group T	Group T
	EN ISO 10582	Type 1	Type 1
Dimensional stability	EN 434	Pass (≤ 0.25%)	Pass (≤ 0.25%)
Acoustic impact noise reduction	EN ISO 717-2/EN ISO 140-8	ΔL <sub>w</sub> = 2 dB	ΔL <sub>w</sub> = 2 dB
Electrical behaviour body voltage	EN 1815	Pass	Pass
Indentation - residual	EN 433	Pass (≤ 0.1 mm)	Pass (≤ 0.1 mm)
Castor chair continuous use	EN 425/ISO 4918	Pass	Pass
Thermal resistance	ISO 8302/EN 12664	0.0147 m <sup>2</sup> K/W	0.0097 m <sup>2</sup> K/W
	Underfloor heating	Suitable. Max 27°C	Suitable. Max 27°C
Slip resistance <sup>2</sup>	EN 13893	DS	DS
	DIN 51130	R10	R10
Light Reflectance Value (LRV)	BS 8493:2008+A1:2010	See separate table	See separate table
Adhesive	Karndean Universal	Yes	Yes
	Acrylic	Yes	Yes
	Epoxy	Yes	Yes
	High Temperature+	Yes	Yes
	Pressure Sensitive	Yes	Yes
Recycling		Suitable	Suitable
Phthalate free		Yes	Yes

<sup>1</sup> Subject to terms. Please see our website.

<sup>2</sup> Slip resistance is measured on freestanding ex-factory product. Slip resistance can be affected by many factors, including but not limited to; product installation and underlayment, surface contamination, use, wear and how the product is maintained. Textural variation along the surface of the product can affect nominal values.


For more information:

UK: 01386 820104 | ROI: 01 6569887

Email: commercial@karndean.co.uk

Visit: www.karndean.com

May 21



Solid Colours



	Product Code	Size	Box Quantity		Slip Resistance DIN 51130	LRV
			m <sup>2</sup>	Pieces		
Solid Colours	V6	Various	N/A	N/A	R10	13
	V7	Various	N/A	N/A	R10	10
	V9	Various	N/A	N/A	R10	4
	V10	Various	N/A	N/A	R10	74
	V11	Various	N/A	N/A	R10	41
	V12	Various	N/A	N/A	R10	21
	V13	Various	N/A	N/A	R10	24
	V14	Various	N/A	N/A	R10	52
	V15	Various	N/A	N/A	R10	36
	V16	Various	N/A	N/A	R10	13
	V17	Various	N/A	N/A	R10	29
	V18	Various	N/A	N/A	R10	12
	V19	Various	N/A	N/A	R10	24
	V20	Various	N/A	N/A	R10	71