

	Standard	Result
Size	ISO 24342	See separate table
Thickness	ISO 24346	3.0 mm
Wear layer	ISO 24340	0.7 mm
Surface treatment		K-Guard+ PU coating
Warranty ¹	Commercial Domestic	20 years wear Lifetime wear
Bevelled edge		Standard
Standards	EN 649/EN ISO 10582 ASTM F1700	Pass Pass
Classification	ISO 10874 - Commercial ISO 10874 - Domestic	34: Commercial very heavy 23: Domestic heavy
Reaction to fire	AS/NZS 9239.1:2003	CRF: Smoke value: Hand Crafted Wood 7.1 kW/m ² 121% min Oak Royale 6.4 kW/m ² 114% min Oak Premier 8.5 kW/m ² 177% min Parquet 8.5 kW/m ² 220% min
Staining resistance	EN ISO 26987/EN 423 ASTM F925	Excellent Pass
Light fastness	ISO 105-B02 ASTM F1515	Pass (≥ 6) Pass (< 8)
Abrasion resistance	EN 660-2 ISO 10582 ASTM D3884	Group T Type 1 Pass
Flexibility	ISO 24344	Pass
Dimensional stability	EN 434/ISO 23999 ASTM F2199	Pass (≤ 0.25%) Pass
Acoustic impact noise reduction ²	EN ISO 717-2/EN ISO 140-8	ΔL _w = 2 dB
Electrical behaviour body voltage	EN 1815	Pass
Indentation - residual	EN 433/ISO 24343-1 ASTM F1914	Pass (≤ 0.1 mm) Pass (< 8%)
Castor chair continuous use	EN 425/ISO 4918	Pass
Thermal resistance	ISO 8302	0.0147 m ² K/W Suitable for underfloor heating. Max 27°C
Slip resistance ³	AS/NZS 4586:2013	See separate table
Adhesive	General use: High temperature:	Karndean Mega-Bond Karndean 8000 2-part Polyurethane
Environmental	GBCA/NZGBC GreenStar Rating System Floorscore SCS-EC10.3-2014 v4.0 Indoor Air Comfort Environmental Product Declaration NSF/ANSI 332 ISO 14001 / ISO 9001	GreenTag Level A; LCA Silver Plus; Best Practice PVC Indoor air quality certified; Compliant low emitting VOC emissions. Gold certification Compliant low emitting VOC emissions. Product-specific Type III EPD (products with external third-party verification) Sustainability Assessment for Resilient Floor Coverings; Conformant product Manufactured to quality and environment management systems standards
Recycling		Suitable
Phthalate free		Yes

¹ Subject to terms. Please see our website.

² Result is Ln,w = 58 dB when installed on Regupol 4515 acoustic underlay.

³ Slip resistance is measured on freestanding ex-factory product. Slip resistance can be affected by many factors, including but not limited to; product installation and underlayment, surface contamination, use, wear and how the product is maintained. Textural variation along the surface of the product can affect nominal values.

For more information:

Australia

Call: 1800 33 11 70

Email: customerservice@karndean.com.au

Visit: www.karndean.com

New Zealand

Call: 0800 44 21 01

Email: customerservice@karndean.co.nz

Visit: www.karndean.com

Jun 22



Product Code	Size		Box Quantity		Slip Resistance
	mm	inches	m ²	Pieces	Oil-Wet Ramp
AP01	228.6 x 76.2	9" x 3"	3.345	192 Planks	R9
AP02	228.6 x 76.2	9" x 3"	3.345	192 Planks	R9
AP03	228.6 x 76.2	9" x 3"	3.345	192 Planks	R9
EW01	914.4 x 152.4	36" x 6"	3.345	24 Planks	R9
EW02	914.4 x 152.4	36" x 6"	3.345	24 Planks	R9
EW03	914.4 x 152.4	36" x 6"	3.345	24 Planks	R9
HCO1	914.4 x 152.4	36" x 6"	3.345	24 Planks	R9
HCO2	914.4 x 152.4	36" x 6"	3.345	24 Planks	R9
HCO3	914.4 x 152.4	36" x 6"	3.345	24 Planks	R9
HCO4	914.4 x 152.4	36" x 6"	3.345	24 Planks	R9
HCO5	914.4 x 152.4	36" x 6"	3.345	24 Planks	R9
HCO6	914.4 x 152.4	36" x 6"	3.345	24 Planks	R9
RL01	1219.2 x 177.8	48" x 7"	3.252	15 Planks	R9
RL02	1219.2 x 177.8	48" x 7"	3.252	15 Planks	R9
RL03	1219.2 x 177.8	48" x 7"	3.252	15 Planks	R9
RL04	1219.2 x 177.8	48" x 7"	3.252	15 Planks	R9

Wood Designs