Technical Data



	Standard	Result
Thickness		3/32" (2.5mm)
Wear layer		20mil (0.5mm)
Warranty	Commercial Residential	10 Years* 15 Years*
Beveled edge		No
Standards	ASTM F1700	
Classification	ASTM F1700	Class III Type B
Reaction to fire	ASTM E648-06	Class 1
Flammability test	FF 170 Federal Approval	Pass
Slip resistance	ASTM C1028	ADA Compliant Dry 0.66 Wet 0.67
Staining resistance	ASTM F925	Pass
Light fastness	ASTM F1515	Pass △E = 5.0
Abrasion resistance	ASTM D3884	124,000 Cycles
Dimensional stability	ASTM F2199	Pass -0.004"/lin.ft
Static load	ASTM F970	2,000 PSI
Flexibility	ASTM F137	Pass
Adhesive		K-91A K-87WS K-91P (HMT) Karndean Epoxy
Recycling		Suitable

*Subject to terms





For more information:

Call: 888-266-4343

Email: info@karndean.com **Visit:** www.karndean.com





